EPDM - Commercial Grade - 60A

Specifications March 2014

Description:	Ethylene Propylene Diene Monomer (EPDM) and SBR blended sheet is a black colored sheet rubber which provides very good resistance to weathering, ozone and UV exposure.
Compound	
<u>Compound:</u>	10% Ethylene Propylene Diene Monomer (EPDM) Base, SBR Black
<u>Color:</u> Weight	
Weight:	Approximate weight per square foot: $1/8$ " weighs 1-1/4 lbs.
Durometer:	60 Shore A, +/- 5
Temperature Range:	-40 F to 212 F
Minimum Tensile:	725 PSI or 5 MPA
Finish:	Smooth
Minimum Elongation:	300%
Gauges:	1/16", 3/32", 1/8", 3/16", 1/4", 3/8", 1/2" (custom gauges up to 2" thick are
	available upon request)
Widths:	36" (custom widths up to 78" are available upon request)
Roll Length:	25' or 50' depending on thickness.
<u>PSA:</u>	Pressure sensitive adhesive can be applied to this product upon request.
Chemical Resistance:	Good resistance to UV rays and ozone. Good resistance to Anti-freeze,
	Synthetic Detergents, Acetone, Boric acid, Ethanol, Formaldehyde, Mercury,
	Potassium Sulfate, Silver Nitrate, Steam (up to 212 Fahrenheit), Saccharin.
	For EPDM Blend's compatibility with your specific medium please consult a
	Rubber-Cal representative.
Applications:	Provides outstanding resistance to weathering, ozone and UV exposure.
	Gasket, bumper and general exterior applications.
Flexibility:	This medium durometer (55-65) sheet rubber offers good pliability and
<u> </u>	elasticity.
Custom Cuts:	In addition to hand fabrication, this product can be fabricated using laser,
<u></u>	die, and water-jet cut. Please submit your drawings for a price quote.
Availability:	Popular gauges are generally in stock.
<u>Arvanaomty.</u>	i opular gauges are generally in stock.



Specifications and/or prices are subject to change without prior notice. © 2014 Rubber-Cal all rights reserved. Rubber-Cal, Inc. 620 West Warner Ave Santa Ana, CA 92707 800-370-9152 www.rubbercal.com